

HR, P & O, CR SHEET

Material subject to availability. Please call your inside sales rep to confirm alloy, specs, and lengths

GAUGE #	EQUIVALENT	HR & P&O LIMITS	CR LIMITS	#/SQ FT
4	0.2242	0.2332-0.2152		9.375
7	0.1793	0.1873-0.1713	0.1883-.1703	7.500
8	0.1644	.1724-.1564	.1734-.1554	6.875
10	0.1345	0.1425-0.1265	.1405-.1285	5.625
11	0.1196	0.1276-0.1116	.1256-.1136	5.000
12	0.1046	0.1126-0.0966	.1106-.0986	4.375
13	0.0897	0.0967- 0.0827	.0947-.0847	3.750
14	0.0747	0.0817-0.0677	.0797-.0697	3.125
16	0.0598	0.0658-0.0538	.0648-.0548	2.500
18	0.0478	.0528-.0428	.0518-.0438	2.000
20	0.0359	.0389-.0329		1.500
22	0.0299	.0329-.0269		1.250
24	0.0239	.0269-.0209		1.000
26	0.0179	.0199-.0159		0.750
28	0.0149	.0169-.0129		0.625

GALV SHEET

Material subject to availability. Please call your inside sales rep to confirm alloy, specs, and lengths

GAUGE #	EQUIVALENT	TOLERANCE RANGE	#/SQ FT
10	0.1382	.1472-.1292	5.78125
11	0.1233	.1323-.1143	5.15625
12	0.1084	.1174-.0994	4.53125
13	0.0934	.1014-.0854	3.90625
14	0.0785	.0865-.0705	3.28125
16	0.0635	.0695-.0575	2.65625
18	0.0516	.0566-.0466	2.15625
20	0.0396	.0436-.0356	1.65625
22	0.0336	.0376-.0296	1.40625
24	0.0276	.0316-.0236	1.15625
26	0.0217	.0247-.0187	0.90625
28	0.0187	.0217-.0157	0.78125
30	0.0157	.0187-.0127	0.65625