

BORRMANN METAL CENTER

HR, P & O, CR SHEET

Material subject to availability. Please call your inside sales rep to confirm alloy, specs, and lengths

GAUGE #	EQUIVALENT	HR & P&O LIMITS	CR LIMITS	#/SQ FT
4	0.2242	0.2332-0.2152		9.375
7	0.1793	0.1873-0.1713	0.1883-.1703	7.500
8	0.1644	.1724-.1564	.1734-.1554	6.875
10	0.1345	0.1425-0.1265	.1405-.1285	5.625
11	0.1196	0.1276-0.1116	.1256-.1136	5.000
12	0.1046	0.1126-0.0966	.1106-.0986	4.375
13	0.0897	0.0967- 0.0827	.0947-.0847	3.750
14	0.0747	0.0817-0.0677	.0797-.0697	3.125
16	0.0598	0.0658-0.0538	.0648-.0548	2.500
18	0.0478	.0528-.0428	.0518-.0438	2.000
20	0.0359	.0389-.0329		1.500
22	0.0299	.0329-.0269		1.250
24	0.0239	.0269-.0209		1.000
26	0.0179	.0199-.0159		0.750
28	0.0149	.0169-.0129		0.625

GALV SHEET

Material subject to availability. Please call your inside sales rep to confirm alloy, specs, and lengths

GAUGE #	EQUIVALENT
10	0.1382
11	0.1233
12	0.1084
13	0.0934
14	0.0785
16	0.0635
18	0.0516
20	0.0396
22	0.0336
24	0.0276
26	0.0217
28	0.0187
30	0.0157

TOLERANCE RANGE	#/SQ FT
.1472-.1292	5.78125
.1323-.1143	5.15625
.1174-.0994	4.53125
.1014-.0854	3.90625
.0865-.0705	3.28125
.0695-.0575	2.65625
.0566-.0466	2.15625
.0436-.0356	1.65625
.0376-.0296	1.40625
.0316-.0236	1.15625
.0247-.0187	0.90625
.0217-.0157	0.78125
.0187-.0127	0.65625

HR PLATE

Material subject to availability. Please call your inside sales rep to confirm alloy, specs, and lengths

THICKNESS	#/SQ FT
3/16"	7.66
1/4"	10.21
5/16"	12.75
3/8"	15.32
7/16"	17.85
1/2"	20.42
9/16"	22.95
5/8"	25.53
3/4"	30.63
7/8"	35.74
1"	40.84
1-1/8"	45.95
1-3/16"	48.45

THICKNESS	#/SQ FT
1-1/4"	51.05
1-3/8"	56.10
1-1/2"	61.26
1-5/8"	66.30
1-3/4"	71.47
2"	81.68
2-1/4"	91.89
2-1/2"	102.00
2-3/4"	112.30
3"	122.40
3-1/4"	132.60
3-1/2"	142.80
3-3/4"	153.00
4"	163.20

HR DIAMOND PLATE

Material subject to availability. Please call your inside sales rep to confirm alloy, specs, and lengths

THICKNESS
14 ga.
1/8"
3/16"
1/4"
5/16"
3/8"
1/2"

#/SQ FT
3.75
6.16
8.70
11.25
13.80
16.35
21.45